

## Abiurana

<b>Durability class</b>	Class 1
<b>Applications</b>	Abiurana wood is used for decking, foundations, hardwood <a href="#">bridge sections</a> and fence posts.
<b>Specific gravity</b>	(1100-)1030- 1170(-1250) kg/m <sup>3</sup> at 12% moisture content, fresh 1280 kg/m <sup>3</sup> .
<b>Colour</b>	The colour of Abiurana hardwood is pinkish brown to reddish.
<b>Details</b>	Faint stripe or flame drawing.
<b>Grain</b>	Straight to irregular, sometimes with a light cross-thread.
<b>Timber texture</b>	Fine.
<b>Hardness</b>	12200 N Janka.
<b>Workability</b>	Difficult for machine work, due to the presence of silica. However, Abiurana tropical hardwood can be made very smooth.
<b>Screwing/nailing</b>	Pre-drilling is necessary.
<b>Finishing of surface</b>	Want to treat Abiurana? Keep in mind that oil or stain is not directly absorbed by the wood.
<b>Botanical name</b>	<i>Pouteria guianensis</i>
<b>Origin area</b>	Tropical South America.
<b>Other names</b>	Abiorana, Caimito, Akoinsiba
<b>Background information</b>	Abiurana wood is listed in NEN 5493.
<b>Family</b>	Sapotaceae