

Abiurana

Durability class	Class 1
Applications	Abiurana wood is used for decking, foundations, hardwood bridge sections and fence posts.
Specific gravity	(1100-)1030- 1170(-1250) kg/m ³ at 12% moisture content, fresh 1280 kg/m ³ .
Colour	The colour of Abiurana hardwood is pinkish brown to reddish.
Details	Faint stripe or flame drawing.
Grain	Straight to irregular, sometimes with a light cross-thread.
Timber texture	Fine.
Hardness	12200 N Janka.
Workability	Difficult for machine work, due to the presence of silica. However, Abiurana tropical hardwood can be made very smooth.
Screwing/nailing	Pre-drilling is necessary.
Finishing of surface	Want to treat Abiurana? Keep in mind that oil or stain is not directly absorbed by the wood.
Botanical name	Pouteria guianensis
Origin area	Tropical South America.
Other names	Abiorana, Caimito, Akoinsiba
Background information	Abiurana wood is listed in NEN 5493.
Family	Sapotaceae