Cedrinho

Durability class	Literature: Slightly durable/Not durable Above ground: Durable.
Specific gravity	Fresh 1000-1100 kg/m3. At 12% moisture content 530-700 kg/m3.
Colour	Gold-red brown towards yellow, giving this hardwood a warm appearance.
Applications	Cedrinho wood is used for several exterior applications, like garden screens, cladding, (interior) doors, furniture and toys.
Hardness	3900 N.
Grain	Straight, sometimes a bit irregular or wavy.
Timber texture	Moderately coarse to coarse.
Stability	Moderately fast to fast.
Drying	Drying goes slowly with less risks.
Workability	Cedrinho hardwood is easy to work with both by hand and by machine.
Details	Cedrinho has a remarkably fine flame pattern.
Screwing/nailing	Pre-drilling is recommended.
Finishing of surface	Good.
Botanical name	Erisma uncinatum
Origin area	The Amazon region of Brazil, Surinam, Guayana, Venezuela.
Other names	Bruteiro, Cambará, Cambará-rosa, Cedrilho.
Background information	The tree has a diameter till 70 cm with about 5 cm wide sapwood.
Family	Vochysiaceae