

## Cedrinho

<b>Durability class</b>	Literature: Slightly durable/Not durable Above ground: Durable.
<b>Applications</b>	Cedrinho wood is used for several exterior applications, like <a href="#">garden screens</a> , cladding, (interior) doors, furniture and toys.
<b>Specific gravity</b>	Fresh 1000-1100 kg/m <sup>3</sup> . At 12% moisture content 530-700 kg/m <sup>3</sup> .
<b>Colour</b>	Gold-red brown towards yellow, giving this hardwood a warm appearance.
<b>Details</b>	Cedrinho has a remarkably fine flame pattern.
<b>Grain</b>	Straight, sometimes a bit irregular or wavy.
<b>Timber texture</b>	Moderately coarse to coarse.
<b>Stability</b>	Moderately fast to fast.
<b>Drying</b>	Drying goes slowly with less risks.
<b>Hardness</b>	3900 N.
<b>Workability</b>	Cedrinho hardwood is easy to work with both by hand and by machine.
<b>Screwing/nailing</b>	Pre-drilling is recommended.
<b>Finishing of surface</b>	Good.
<b>Botanical name</b>	<i>Erisma uncinatum</i>
<b>Origin area</b>	The Amazon region of Brazil, Surinam, Guayana, Venezuela.
<b>Other names</b>	Bruteiro, Cambará, Cambará-rosa, Cedrilho.
<b>Background information</b>	The tree has a diameter till 70 cm with about 5 cm wide sapwood.
<b>Family</b>	Vochysiaceae