Dapalo

Durability class	Moderately durable.
Specific gravity	1000-1100 kg/m3. Dried to 12% Moisture content: ± 850 kg/m3
Colour	Yellow green brown.
Applications	Dapalo hardwood is mainly used for garden timber like decking and fencing.
Strength class	Unknown.
Hardness	7200-9300N according to Janka
Grain	The grain is straight to sometimes irregular or interlocked.
Timber texture	The texture is medium coarse.
Stability	Moderate
Drying	Drying should be done slowly and with caution, as there is a chance of cracking or warping.
Workability	Machining goes well with Dapalo hardwood and the surface will get nice and smooth.
Details	The heartwood of Dapalo has a beige brown colour with a green shade. Sometimes small black stripes appear. The sapwood is easy to distinguish.
Screwing/nailing	Pre-drilling is recommended.
Finishing of surface	Gluing and finishing are reported to be good.
Botanical name	Buchenavia tetraphylla
Other names	Heavy Tanimbuca, Nargusta .
Family	Combretaceae