

Jutai

Durability class Class 1-2.

Specific gravity Freshly cut 950-1200 kg / m3. At 12% moisture content from 750 to 900 kg / m3.

Colour Jutai wood has a dark reddish brown colour.

Jutai hardwood is suitable for furniture, floors, facades, panelling and is often used decoratively **Applications**

because of the beautiful veins.

Grain Straight, sometimes irregular threads and light cross-thread.

Timber texture Fine to moderately coarse.

Stability Average.

Drying Jutai wood dries slowly.

Workability Fairly easy to work with and finish. **Details** This wood has a beautiful fine pattern.

Screwing/nailing Pre-drilling is necessary for Jutai hardwood.

Botanical name Martiodendron parviflorum

Origin area Tropical Central America and South America.

This tropical wood is often confused with Jatoba hardwood. **Background information**