Jutai

Durability class	Class 1-2.
Specific gravity	Freshly cut 950-1200 kg / m3. At 12% moisture content from 750 to 900 kg / m3.
Colour	Jutai wood has a dark reddish brown colour.
Applications	Jutai hardwood is suitable for furniture, floors, facades, panelling and is often used decoratively because of the beautiful veins.
Grain	Straight, sometimes irregular threads and light cross-thread.
Timber texture	Fine to moderately coarse.
Stability	Average.
Drying	Jutai wood dries slowly.
Workability	Fairly easy to work with and finish.
Details	This wood has a beautiful fine pattern.
Screwing/nailing	Pre-drilling is necessary for Jutai hardwood.
Botanical name	Martiodendron parviflorum
Origin area	Tropical Central America and South America.
Background information	This tropical wood is often confused with Jatoba hardwood.