

## Louro Gamela / Red Louro

<b>Durability class</b>	Class 1-2.
<b>Specific gravity</b>	Fresh 800-1000 kg/m <sup>3</sup> . At 12% moisture content 650-750 kg/m <sup>3</sup> .
<b>Colour</b>	Louro gamela has a red to brownish colour. Without finish and with good ventilation, the wood will turn into a silvery gray within a year.
<b>Applications</b>	The wood can be used for <a href="#">street furniture</a> , facade cladding, decking, <a href="#">fence boards</a> .
<b>Strength class</b>	D24
<b>Hardness</b>	2950 N.
<b>Grain</b>	Straight to interlocked grain, sometimes tousled.
<b>Timber texture</b>	The grain of red Louro wood is moderately coarse.
<b>Stability</b>	Average.
<b>Drying</b>	Louro Gamela hardwood is a very slow-drying type of wood. Thin wood dries moderately quickly. It has to be dried carefully to avoid cracks and bending. Wood thicker than 50 mm is very difficult to dry due to the waxy substance which soaks its surface.
<b>Workability</b>	The machinability of Louro vermelho is good, but it has a slightly dulling effect on tools.
<b>Details</b>	Freshly sawn wet Louro gamela wood has a distinctive scent, which disappears after drying. The wood weave of wet Louro gamela is covered with a waxy substance, which makes it difficult for the wood to absorb or release moisture.
<b>Screwing/nailing</b>	Machining goes well. With sharp tools a smooth surface can be achieved. Pre-drilling is recommended.
<b>Finishing of surface</b>	With glueing (also for finger jointing) the results are good. Research is going on for glueing of Louro Gamela in constructive uses. Finishing goes well.
<b>Botanical name</b>	Sextonia rubra
<b>Origin area</b>	Brazil, Guyana and Suriname.
<b>Other names</b>	Louro vermelho, canela (Brazil), red louro wood (Great Britain), wana (Suriname).
<b>Background information</b>	Freshly sawn, Louro Gamela heartwood has a salmon hue which turns to a light reddish brown or a slightly yellowish reddish brown once dried. This wood has a moderately distinct golden sheen. The 20-50 mm wide sapwood has a yellowish white to dirty yellow or grey-brown colour which is clearly different from the heartwood. The wood can have a light stripe pattern due to cross-grained texture, which makes it look somewhat like mahogany.
<b>Remarks</b>	The large tree has a diameter up to 1,2 m, with a straight and cylindric shape. It is possible to produce larger dimensions.
<b>Family</b>	Lauraceae
<b>Projects</b>	<a href="#">Stairs Mijnsheerlyckheid</a> , <a href="#">Cladding chalets Camping de Brem</a> , <a href="#">Garden fence Zaltbommel</a> , <a href="#">Facade cladding modern house</a> .