

Muiracatiara

Durability class	Class 1.
Specific gravity	Fresh 1200-1250 kg/m ³ . At 12% moisture content 750-900 kg/m ³ .
Colour	Red with black stripes. This type of wood is therefore called Tigerwood.
Applications	Muiracatiara hardwood is widely used because of its decorative appearance and typical hardwood properties (durable and strong). You will often see this hardwood in horizontal railings, facades, bridge decks and sheet piling . When planed, it becomes very slippery and has a greasy feeling.
Strength class	D40.
Brandklasse gevel	D, en B mogelijk met Forestlines®
Hardness	7700-9600 N.
Grain	Straight to cross-thread, sometimes slightly wavy.
Timber texture	Fine to moderately coarse.
Stability	Low to medium.
Drying	Natural drying in the open air can be done without any problems. Accelerated drying of Tigerwood can lead to surface cracks.
Workability	The Muiracatiara FSC wood is easy to work with, despite the high density. Gluing is reasonably easy and we have good experiences with finishing. Pre-drilling is recommended. The wood dries fairly quickly, but this process must be done carefully to avoid surface cracks in thin wood and longitudinal cracks in thicker wood.
Details	The colour of the heartwood is light orange-brown, with a variable proportion of dark brown 'veins'. This makes Muiracatiara wood particularly decorative. After exposure to sunlight, the wood quickly turns to an orange-reddish brown to deep red brown. The sapwood is easily distinguishable as it has a straight grain with few irregularities. The grain is fine.
Screwing/nailing	Good. Pre-drilling is necessary.
Finishing of surface	Good with lacquer and varnish. After sanding, finishing and/or lacquering, it can show its beautiful pattern.
Botanical name	Astronium spec. div.
Origin area	Muiracatiara hardwood grows in Tropical Central America and South America.
Other names	Gonçalo alves, Kingwood, Tigerwood.
Quality requirements	Muiracatiara is mentioned in the NEN 5493 'Quality requirements for hardwood in earth, road and hydraulic engineering works and other constructive applications.
Remarks	FSC® certified Muiracatiara hardwood is available in the Amazon region of Brazil. The trees have a diameter till about 0,6 -1,0 m, with a straight and cylindrical shape and a trunk of about 14-18 m. The sapwood is about 4-10 cm wide
Family	Anacardiaceae
Forestlines®	Muiracatiara hardwood is available in the Forestlines® profile