

Pakan

| | |
|-----------------------------|---|
| Durability class | Class 1-2. |
| Specific gravity | Freshly cut 1050-1150 kg / m3. At 12% moisture content of 850-900 kg / m3. |
| Colour | Pakan hardwood has a yellow to light brown colour. |
| Applications | Pakan wood is often used for facade cladding , decking, truck floors, interior panelling and indoor floors. |
| Strength class | Unknown. |
| Grain | Straight. |
| Timber texture | Moderate to coarse. |
| Drying | Careful drying is advised. |
| Workability | In general, Pakan wood has moderate machinability. |
| Details | Pakan has a beautiful pattern. |
| Screwing/nailing | Pre-drilling Pakan hardwood is necessary. |
| Finishing of surface | Good. |
| Botanical name | Platonia insignis |
| Origin area | Surinam, French Guinea, Brazil. |
| Other names | Yellow Heart. |
| Family | Guttiferae |