Pakan

Durability class	Class 1-2.
Specific gravity	Freshly cut 1050-1150 kg / m3. At 12% moisture content of 850-900 kg / m3.
Colour	Pakan hardwood has a yellow to light brown colour.
Applications	Pakan wood is often used for facade cladding, decking, truck floors, interior panelling and indoor floors.
Strength class	Unknown.
Grain	Straight.
Timber texture	Moderate to coarse.
Drying	Careful drying is advised.
Workability	In general, Pakan wood has moderate machinability.
Details	Pakan has a beautiful pattern.
Screwing/nailing	Pre-drilling Pakan hardwood is necessary.
Finishing of surface	Good.
Botanical name	Platonia insignis
Origin area	Surinam, French Guinea, Brazil.
Other names	Yellow Heart.
Family	Guttiferae