

Pakan

Durability class	Class 1-2.
Strength class	Unknown.
Applications	Pakan wood is often used for facade cladding , decking, truck floors, interior panelling and indoor floors.
Specific gravity	Freshly cut 1050-1150 kg / m3. At 12% moisture content of 850-900 kg / m3.
Colour	Pakan hardwood has a yellow to light brown colour.
Details	Pakan has a beautiful pattern.
Grain	Straight.
Timber texture	Moderate to coarse.
Drying	Careful drying is advised.
Workability	In general, Pakan wood has moderate machinability.
Screwing/nailing	Pre-drilling Pakan hardwood is necessary.
Finishing of surface	Good.
Botanical name	Platonia insignis
Origin area	Surinam, French Guinea, Brazil.
Other names	Yellow Heart.
Family	Guttiferae